

Tetric EvoFlow®

1

Self-Etch



Etch & Rinse



or




or



Selective Enamel-Etch

2

Adhese® Universal
VivaPen®



3s

Bluephase®
PowerCure

3

Tetric®
EvoFlow®



3s

4

Tetric® Prime



or

Tetric® PowerFill



3s

mW/cm ²	Tetric Prime/ Tetric EvoFlow	Tetric PowerFill/ Tetric PowerFlow	Adhese Universal
500 – 900	20 s	20 s	10 s
900 – 1400	10 s	10 s	10 s
1800 – 2200	5 s	5 s	5 s
Direct posterior restoration, light-cured from occlusal aspect Direkte Seitenzahnrestauration, okklusale Belichtung			
2700 – 3300	–	3 s	3 s

ivoclar
vivadent®
clinical

Tetric EvoFlow®

Conventional composites				4-mm-composites	
FLOWABLE		SCULPTABLE		FLOWABLE	SCULPTABLE
Tetric EvoFlow®		Tetric® Prime		Tetric® PowerFlow	Tetric® PowerFill
					
Dentin & Bleach XL	Enamel	Dentin	Enamel	Dentin-like translucency	Enamel-like translucency
1.5 mm	2 mm	1.5 mm	2 mm	4 mm	4 mm
20 s				20 s	
10 s				10 s	
5 s				5 s	
—				3 s	

3s



CE 0123

Date information prepared: 2019-12-10/64 1319/Rev. 4
Ivoclar Vivadent AG, 9494 Schaan/Liechtenstein

ivoclar
vivadent
clinical